



Clyrell RC5056

Polypropylene, Random Copolymer

Product Description

Developmental Grade *Clyrell* RC5056 is a polypropylene random copolymer. With its high gloss and excellent clarity, combined with its balance of rigidity and impact, this grade is particularly suitable for injection molding of high clarity containers. Potential end use applications include housewares and food containers. This is a preliminary Product Data Sheet.

Product Characteristics

Status	Commercial: Active
Test Method used	ASTM
Availability	Asia-Pacific, Australia/NZ, Africa-Middle East
Processing Method	Injection Molding
Features	High Clarity, Random Copolymer, High Gloss
Typical Customer Applications	Housewares, Clear Containers

Typical Properties	Method	Value	Unit
Physical			
Density -Specific Gravity	ASTM D 792	0.9	g/cm ³
Melt flow rate (230°C/2.16kg)	ASTM D 1238	10	g/10 min
<i>Note: ASTM D1238L</i>			
Mechanical			
Tensile Strength @ Yield	ASTM D 638	350	kg/cm ²
Flexural Modulus	ASTM D 790	14000	kg/cm ²
Tensile Elongation @ Yld	ASTM D 638	10	%
Impact			
Notched izod impact (23 °C)	ASTM D 256	5	kg-cm/cm
Hardness			
Rockwell Hardness (R Scale)	ASTM D 785	102	
Thermal			
Vicat softening point	ASTM D 1525	134	°C
Heat deflection temperature at 0.46 N/mm ²	ASTM D 648	100	°C
Optical			
Haze	ASTM D 1003	9	%
<i>Note: 2mm sample thickness</i>			

Notes

Typical properties; not to be construed as specifications.

© LyondellBasell Industries Holdings, B.V. 2011

LyondellBasell markets this product through the following entities:

- Equistar Chemicals, LP
- Basell Sales & Marketing Company B.V.
- Basell Asia Pacific Limited
- Basell International Trading FZE
- LyondellBasell Australia Pty Ltd

For the contact details of the LyondellBasell company selling this product in your country, please visit <http://www.lyondellbasell.com/>.

Before using a product sold by one of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally. SELLER MAKES NO WARRANTY; EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE) OTHER THAN AS SEPARATELY AGREED BETWEEN THE PARTIES IN WRITING. This product(s) may not be used in the manufacture of any US FDA Class III Medical Device or Health Canada Class IV Medical Device and may not be used in the manufacture of any US FDA Class II Medical Device or Health Canada Class II or Class III Medical Device without the prior written approval by Seller of each specific product or application.

Users should review the applicable Material Safety Data Sheet before handling the product.

Addhere, Adflex, Adstif, Adsyl, Akoafloor, Akoalit, Alastian, Alathon, Alkylate, Amazing Chemistry, Aquamarine, Aquathene, Arconate, Arcopure, Arcosolv, Arctic Plus, Arctic Shield, Avant, Catalloy, Clyrell, CRP, Crystex, Dexflex, Duopac, Duoprime, Explore & Experiment, Filmex, Flexathene, Fueling the Power to Win, Get in touch with, Glacido, Hifax, Histif, Hostacom, Hostalen, Ideal, Integrate, Koattro, LIPP, Lucalen, Luflexen, Lupolen, Lupolex, Luposim, Lupostress, Lupotech, Metocene, Microthene, Moplen, MPDIOL, Nerolex, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Pro-Fax, Punctilious, Purell, SAA100, SAA101, Sequel, Softell, Spherilene, Spheripol, Spherizone, Starflex, Stretchene, Superflex, TBac, Tebol, T-Hydro, Toppyl, Trans4m, Tufflo, Ultrathene, Vacido and Valtec are trademarks owned or used by the LyondellBasell family of companies.

Adsyl, Akoafloor, Akoalit, Alastian, Alathon, Aquamarine, Arconate, Arcopure, Arcosolv, Arctic Plus, Arctic Shield, Avant, CRP, Crystex, Dexflex, Duopac, Duoprime, Explore & Experiment, Filmex, Flexathene, Hifax, Hostacom, Hostalen, Ideal, Integrate, Koattro, Lucalen, Lupolen, Microthene, Moplen, MPDIOL, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Pro-Fax, Punctilious, Purell, Sequel, Softell, Spheripol, Spherizone, Starflex, Tebol, T-Hydro, Toppyl, Tufflo and Ultrathene are registered in the U.S. Patent and Trademark Office.

Release Date: 14 Sep 2009